

Friday, February 26, 2021 10:36 AM EST

Tidewater, INC
 MD-019
 12100 Greenspring Ave
 Owings Mills MD 21117-1610
 (410) 540-8700

Report Number: 360356
 Recorded By: Paul Giammanco
 (301) 721-2663
 pgiammanco@bondwater.com
 On-Site Time: 9:00 AM EST to 9:30 AM EST

MD-019 - Closed Loops

Test	Hot Loop	Chilled Glycol Loop		
Conductivity (as mmhos)	1050 3500 max	3500 3500 max		
pH	8.4 8 - 10.5	8.5 8 - 10		
Molybdate (ppm as Mo)	200 50 - 200	75 50 - 200		

Opening Comment

Performed service visit.

Hot Water Loop

Online 

Performed all tests for hot water loop. All readings were within desired range, providing optimal corrosion protection.

Chill Water Glycol Loop

Online 

Performed all tests for chilled glycol system. All readings were within desired range, providing optimal corrosion protection.

Bond Water Technologies, Inc. recommends that you perform regular and/or daily analysis to control chemical levels and cycles of concentration within established limits. Test results reflect conditions during the point in time when the analysis was performed. Additional testing may be performed upon request. As operating conditions vary, test results will change over time. In no event shall Bond Water Technologies, Inc. be liable for any incidental, direct or indirect, consequential or special damages of any kind.

Bond Water Technologies, Inc. - 630 East Diamond Avenue, Suite J / K, Gaithersburg MD 20877 (301) 721-2663