

Tidewater, INC
VA-701
886 Carolina Road
Suffolk Virginia 23434-6040
(410) 540-8700

Recorded By: Jon Miller
(301) 580-9820
jmillier@bondwater.com

Mechanical Room - HVAC Equipment

Test	Hot Loop	Chill Loop		
Conductivity (as mmhos)	3445 4000 max	3050 4000 max		
pH	10.3 8 - 10.5	9.9 8 - 10.5		
Sodium Nitrite (ppm as NaNO ₃)	1400 600 - 2000	1520 400 - 2000		

Hot Water Loop

Online 

Corrosion inhibitor residual is excellent at this time providing excellent corrosion protection.

Chill Water Loop

Online 

Corrosion inhibitor residual is excellent at this time providing excellent corrosion protection.