

Tidewater, INC
VA-701
886 Carolina Road
Suffolk Virginia 23434-6040
(410) 540-8700

Recorded By: Jon Miller
(301) 580-9820
jmillier@bondwater.com

Mechanical Room - HVAC Equipment

Test	Hot Loop	Chill Loop		
Conductivity (as mmhos)	3442 4000 max	2740 4000 max		
pH	10.1 8 - 10.5	10.0 8 - 10.5		
Sodium Nitrite (ppm as NaNO ₃)	1360 600 - 2000	1440 400 - 2000		

Opening Comment

Performed scheduled service visit.

Took a sample of chill water loop glycol to verify condition in laboratory.

Hot Water LoopOnline 

Corrosion inhibitor residual is excellent at this time providing excellent corrosion protection.

Chill Water LoopOnline 

Corrosion inhibitor residual is excellent at this time providing excellent corrosion protection.